Alpha Industry Company Limited

Qingzhou Economic Development Zone,Qingzhou,Weifang,Shandong,China
http://www.petfilmchina.com Email: inquire@petfilmchina.com

Pet Film Test Report

Thickness	100 mic		Application	For Printing	
Inspector	1		Grade	First Grade	
Test Condition	Temperature:25 ℃ Humidity:50%		Date		
Test Result					
Item		Unit	Value	Mark	Method
Thickenss	TD	mic	100.1		GB/T 6672
Tensile Strength	MD	N/MM2	196		GB/T1040.3
	TD	N/MM2	200		
Tensile elongation at break	MD	%	131		
	TD	%	100		
Haze	TD	%	25		GB/T 2410-2008
Gloss	TD	%	130.6		GB/T 8807
Heat Shrink (150℃/30min)	MD	%	1.5		GB/T 16958 6.5.2
	TD	%	0.5		
Wetting Tension	Corona Treatment	mN/m	52		GB/T 14216